



CEWELD AA DUR 800

TYPE High Molybdenum Cobalt based fluxcored wire for overlay welding against high temperature wear, thermal shock and erosion.

ANWENDUNGEN Metal forming, high temperatures, punching dies seamless pipe manufacturing, mechanical seals, valve seats and trims.

EIGENSCHAFTEN Excellent gliding properties against metal to metal wear due to its low friction, Excellent against erosion, corrosion and galling. The alloy is high temperature resistant up to 1000°C and can resist severe shock and impact at these temperatures.

KLASSIFIKATION AWS A 5.21: ERCCoCr-A
EN ISO 14700: ~E Co1

GEEIGNET FÜR Cladding seats and valves in extreme high temperaure engines, hot sharing blades, hot punching dies, extrusion parts

ZULASSUNGEN

SCHWEISSPOSITIONEN



**TYPISCHE CHEMISCHE
ANALYSE DES
SCHWEISSMETALLS (%)**

C	Si	Cr	Ni	Mo	Fe	Co
0.03	0.3	17	2.4	22	3	Rem.

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				55 HRc

RÜCKTROCKNUNG Not required

GAS ACC. EN ISO 14175 M13



CEWELD AA DUR 800

AA DUR 800 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663424532