



CEWELD CuAl9Fe Tig

TYPE	Copper-Aluminium welding TIG rods					
ANWENDUNGEN	Joint welds or building up of aluminum bronze. Cladding components undergoing metal to metal wear. Joining steel to copper alloys, cast iron and or bronze.					
EIGENSCHAFTEN	Special alloyed copper rods for Tig welding. The weld metal is a Cu-Al bronze. Sound, pore free deposits.					
KLASSIFIKATION	AWS	A 5.7: ERCuAl-A2				
	EN ISO	24373: Cu 6180 / CuAl10Fe				
	W.Nr.	2.0937				
	F-nr	36				
GEEIGNET FÜR	Suitable for seawater resistant applications. Joining steel to copper alloys, cast iron and or bronze. Excellent for metal spraying. Ship propellers, shipbuilding, pump building, shafts, guide grooves etc, UNS : C 60600 - C 61600 - C 68700, DIN : Cu Al5 - Cu Al8 - CuZn20Al2, Werkstoff Nr : 2.0916 - 2.0920 - 2.0960					
ZULASSUNGEN						
SCHWEISSPOSITIONEN	      					
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	Si	Fe	Cu	Zn	Pb	Al
	0.064	0.94	Rem.	0.007	0.015	9.21
MECHANISCHE GÜTEWERTE	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness	
	As Welded		500	35	140 HB	
RÜCKTROCKNUNG	Not required					
GAS ACC. EN ISO 14175	I1					



CEWELD CuAl9Fe Tig

CUAL9FE TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663408914
CUAL9FE TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663408945
CUAL9FE TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663408969
CUAL9FE TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663409003