



CEWELD ERTi-12 Tig

TYPE	Titanium Tig welding wire grade 12						
APPLICATIONS	This alloy finds his applications in chemical industry and offers excellent Weldability. Often recommended for pressure vessels and piping for its superior strength alone.						
PROPERTIES	ERTi-12. Grade 12 (Ti 0.8Ni0.3Mo) is an intermediate strength grade originally developed to provide enhanced crevice-corrosion resistance in high temperature brines, but at lower cost than Grade 7. The improved performance is believed to be the result of Ni++ and Mo++ ions that alter the surface electrochemistry of the material in the crevice or under a surface deposit. Grade 12 has better elevated temperature properties than Grade 2 or 3 and is sometimes specified for pressure vessels or piping for its superior strength alone.						
CLASSIFICATION	AWS	A 5.16: ERTi-12					
	EN ISO	24034: S Ti 3401 / TiNi0,7Mo0,3					
	W.Nr.	~3.7105					
	F-nr	51					
SUITABLE FOR	3.7105 Titanium grade 12, Grade 7, Grade 2 and Grade 3 R56400 Ti3AL-1,5Mn						
APPROVALS							
WELDING POSITIONS	 PA  PB  PC  PD  PE  PF  PG						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	H	N	O	Fe	Ni	Ti
	0.02	0.005	0.01	0.12	0.1	0.8	Rem.
MECHANICAL PROPERTIES	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	
	As Welded		345	480	20	HRc	
REDRYING	Not required						
GAS ACC. EN ISO 14175	I1						



CEWELD ERTi-12 Tig

ERTI-12 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	2,5	8720663406477
ERTI-12 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	2,5	8720663406484
ERTI-12 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	2,5	8720663406491
ERTI-12 TIG 3.2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	2,5	8720663406507