



CEWELD AA NiCrMo 625B

TYPE	Basic flux-cored nickel base welding wire for gas shielded arc welding.								
APPLICATIONS	AA Nicro 625B is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels and for joining 6% molybdenum super austenitic steels.								
PROPERTIES	Latest generation basic slag guarantees optimum metallurgical quality and attractive welder appeal. The weld deposit meets the NiCrMo-3 requirements.Better bead aspect and shape compare to solid wires with better arc stability and improved wetting properties with less spatters.								
CLASSIFICATION	AWS	A 5.34: E NiCrMo3T1-4							
	EN ISO	12153-A: T Ni 6625 (NiCr22Mo9Nb) B M21 3							
	F-nr	43							
	FM	6							
SUITABLE FOR	Ni 6625 / NiCr22Mo9Nb / 2.4831 1.4547 - 1.4876 - 1.4958 - 2.4816 - 2.4856 - 2.4858 - 1.5656 - 1.4529 - 1.4539 - 2.4660 X1CrNiMoCuN20-18-7 - X10NiCrAlTi32-20 - X5NiCrAlTi31-20 - NiCr15Fe - NiCr22Mo9Nb - NiCr21Mo - X1NiCrMoCuN25 20 6 - X1NiCrMoCuN25 20 5 - NiCr21Mo - 8XNi9 UNS: S31254 - N08800 - N08810 - N06600 - N06625 - N08825 - N08926 - N08020 ASTM A 553 Gr.1, Alloy 600, Alloy 600 L, Alloy 625, Alloy 800 / 800H, Alloy 825 Alloy 254SMO - Sanicro 28 - 6Mo								
APPROVALS									
WELDING POSITIONS									
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Ni	Mo	Nb	Fe	S
	0.03	0.35	0.45	21.5	60.5	9.5	3.4	4	0.01
MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness	
					-196°C				
	As Welded	500	780	40	60			HRc	
REDRYING	140°C / 24 hr								
GAS ACC. EN ISO 14175	M21								