



CEWELD CuAl5Ni2

TYPE Copper aluminium nickel alloy for Mig welding and brazing

APPLICATIONS Low alloyed aluminum bronze, particularly suitable for joint welds on ferritic and austenitic steels. Good flowing properties with good cover groove, also suitable for joint welds on steels and copper. For multiplayer welding on steels, pulsed arc welding is recommended. Amazing results are obtained on stainless steel sheet metal due to less heat input, higher travel speed and less cleaning hours. Containers, valve control chambers, exhaust parts, thin sheet welding (steel and specially stainless steel) Ship propellers, shipbuilding, pump building, shafts, guide grooves etc.

PROPERTIES Sound, pore free deposits on ferrous and non-ferrous base materials with excellent wetting. Due to the excellent wetting and low melting point welding speeds can be achieved upto 2 mtr/min. The weld deposit offers a corrosion resistance similar to AISI 304.

CLASSIFICATION EN ISO 24373: Cu 6161 / CuAl5Ni2Mn
F-nr 36

SUITABLE FOR W.Nrs: 2.0916, 2.0920, 2.0928, 2.0932, 2.0936, 2.0940, 2.0960, 2.0962, 2.0966, 2.0970, 2.0978, 2.0980.

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


Mn	Al	Ni+Co
0.5	5	1.8

MECHANICAL PROPERTIES

Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded		353	45	161	HRc

REDRYING Not required

GAS ACC. EN ISO 14175 11



CEWELD CuAl5Ni2

CUAL5NI2 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663409140