



CEWELD Nicro FM 53MD Tig

TYPE	Nickel based filler metal against extreme temperature conditions.								
TOEPASSINGEN	CEWELD NiCro FM 53MD is used for the gas-tungsten-arc and gas-metal-arc welding of INCONEL alloy 693, and the overlaying of carbon steels and stainless steels to provide a nickel-chromium-aluminum alloy corrosion resistant surface.								
EIGENSCHAPPEN	Excellent welding properties with high build-up capacity and low dilution rate. Excellent resistance against temperature cycling conditions exceeding 1200°C and carburized medias. Excellent fatigue strength and creep properties. The high chromium and aluminum levels provide excellent resistance to metal dusting in chemical and petrochemical applications. The product also provides excellent resistance to carburization, sulfidation, and other high temperature corrosion forms Welding similar alloys that have to resist extreme high temperature and for cladding steels or stainless steels to obtain a high temperature resistant surface against oxidation.								
CLASSIFICATIE	AWS	A 5.14: ERNiCrFeAl-1							
	EN ISO	18274: S Ni 6693(NiCr29Fe4Al3)							
	F-nr	43							
	FM	6							
GESCHIKT VOOR	Cladding against high temperature, radiant heater tubes, furnace rolls, muffles in bright annealing furnaces (H2 atmosphere), rotary kilns, pipe hangers, waste gas components, hydrogen production, methanol and ammonia synthesis, Inconel alloy 693								
GOEDKEURINGEN	CE								
LASPOSITIES	PAPBPCPDPEPFPG								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Nb	Fe	Al	Nb+Ta
	0.1	0.4	0.8	30	60	2	4	3.5	2
MECHANISCHE WAARDEN	Heat Treatment			R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded				760	45	HRc		
HERDROGEN	Not required								
GAS ACC. EN ISO 14175	I1								



CEWELD Nicro FM 53MD Tig

NICRO FM 53MD TIG 2,4 X
914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418289